


# Baltic Plus




## Colour Range



Froth




Shake




Chalk



Lusta




Linen




Pumice




Nordic



Cosmos



Night sky



Oxford

## Internal Translucent & Blockout Fabric

Roller Blind | Roman Shade | Panel Glide | Vertical Blind  
89mm, 127mm & 3.0m widths

# Baltic Plus

## Technical Information

	Translucent	Blockout
<b>Composition:</b>	100% Polyester	100% Polyester
<b>Thickness:</b>	0.59mm ± 10%	0.82mm ± 10%
<b>Weight:</b>	220 gsm ± 30 gsm	475 gsm ± 30 gsm
<b>Cutting*:</b>	Ultrasonic cut	Ultrasonic, Aeronaut cut
<b>Colourfastness:</b>	6-7 Blue Scale (AS 2001.4.21)	
<b>Features:</b>	Duraguard® Fabric Protector effectively repels most stain causing agents with its proven, water based, preventative, formula. This fabric protection is totally invisible and has high levels of stain repellence. It makes cleaning and maintaining the fabric much easier. Proudly Made in Australia	
<b>Fire Retardancy Information for NON FR Products^:</b>	Suitable for all building classes <b>except</b> Class 9(b) entertainment venues. A summary of BCA requirements can be provided on request. ^ Fabrics which are not FR treated, have been FR tested and have a Flammability result over 6 or fabrics which are not FR treated and have not undergone FR testing.	

Range:	Item:	Width:	Roll Length:
	Translucent - 82.054.9XX	89mm	100 metres
	Translucent - 82.055.9XX	127mm	100 metres
	Translucent - 82.416.9XX	3000mm	25 metres
	Blockout - 82.417.9XX	3000mm	20 metres

**Care & Cleaning** Dusting with a feather duster is all that is required to keep your fabric looking good. For the removal of stains, dirt and grime, gently wipe fabric skins with a sponge soaked in lukewarm water. If marks are still visible, add a little detergent. Then dry gently with a clean cloth. Test in inconspicuous area before spot cleaning.

## Thermal & Visual Properties

Colour	Thermal Comfort			Glazing & Fabric				Visual Comfort TL / TV
	Ts	Rs	As	GTOT A	GTOT B	GTOT C	GTOT D	
<b>Translucent</b>								
Oxford	21	28	51					4
Jute	26	35	39					12
<b>Blockout</b>								
Oxford	0	19	81					0
Jute	0	25	75					0

Solar protection indicators are laboratory-tested. The most relevant and widely used thermal comfort factors include:

### THERMAL COMFORT

Fabric Only  
Ts Solar Transmittance (%)  
Rs Solar Reflectance (%)  
As Solar Absorbance (%)  
*Solar radiation is always partially transmitted through, absorbed or reflected by the fabric. The sum of all 3 equals 100. Ts + Rs + As = 100% of solar energy.*

### GLAZING & FABRIC

Test data has been supplied using the following glazing types:  
•A Clear single glazing (4mm float)  
•B Clear double glazing (4mm float + 12mm space + 4mm float)  
•C Double glazing low-e coating and argon filled (4mm float + 16mm space + 4mm float)  
•D Reflective double glazing with low-e coating and argon filled (4mm + 16mm space + 4mm float)

### GTOT (RANGE 0-1)

The Solar Heat Gain Coefficient (SHGC), measures the window's (fabric and glass) ability to transmit solar energy into a room. The SHGC is commonly referred to as g-tot. SHGC/g-tot is a calculation of the g-values of the solar protection device (fabric) and the glazing (A, B, C, D). The lower the GTOT value, the greater its ability to insulate against solar heat build-up.

### VISUAL COMFORT

Fabric Only  
TL / TV Light Transmittance (%)  
RL Light Reflectance (%)

*The fenestration property tests were conducted in accordance with EN 410 (1998), EN 14501:(2005), and EN 14500:(2008).*

For more information contact us on:  
hdcustservice@hunterdouglas.com.au

turnilscollage.com.au